

Matériaux en tôle

Charte de tolérance



Gauge	ALC	ALC Tol	ALF	ALF Tol	AG	AG Tol	INOX	INOX Tol	ALUM	ALUM Tol
3	0.2391	+/- .009	0.2391				0.25		0.2294	+/-0.011
4	0.2242	+/- .009	0.2242				0.2344		0.2043	+/-0.011
5	0.2092	+/- .009	0.2092				0.2187		0.1819	+/- .009
6	0.1943	+/- .009	0.1943				0.2031		0.162	+/- .009
7	0.1793	+/- .008	0.1793	+/- .008			0.1875	+/- .007	0.1443	+/- .007
8	0.1644	+/- .008	0.1644	+/- .008			0.165	+/- .007	0.1285	+/- .007
9	0.1495	+/- .008	0.1495	+/- .008	0.1532	+/- .009	0.1562	+/- .007	0.1144	+/- .006
10	0.1345	+/- .008	0.1345	+/- .006	0.1382	+/- .009	0.1406	+/- .006	0.1019	+/- .006
11	0.1196	+/- .008	0.1196	+/- .006	0.1233	+/- .009	0.125	+/- .005	0.0907	+/- .0045
12	0.1046	+/- .008	0.1046	+/- .006	0.1084	+/- .009	0.1094	+/- .005	0.0808	+/- .0045
13	0.0897	+/- .007	0.0897	+/- .005	0.0934	+/- .008	0.0937	+/- .004	0.072	+/- .004
14	0.0747	+/- .007	0.0747	+/- .005	0.0785	+/- .008	0.0781	+/- .004	0.0641	+/- .004
15	0.0673	+/- .006	0.0673	+/- .005	0.071	+/- .006	0.0703	+/- .004	0.0571	+/- .0035
16	0.0598	+/- .006	0.0598	+/- .005	0.0635	+/- .006	0.0625	+/- .003	0.0508	+/- .0035
17	0.0538	+/- .006	0.0538	+/- .004	0.0575	+/- .005	0.0562	+/- .003	0.0453	+/- .0035
18	0.0478	+/- .005	0.0478	+/- .004	0.0516	+/- .005	0.05	+/- .003	0.0403	+/- .003
19	0.0418	+/- .004	0.0418	+/- .004	0.0456	+/- .005	0.0437	+/- .003	0.0359	+/- .003
20	0.0359	+/- .003	0.0359	+/- .003	0.0396	+/- .004	0.0375	+/- .002	0.032	+/- .0025
21	0.0329	+/- .003	0.0329	+/- .003	0.0366	+/- .004	0.0344	+/- .002	0.0285	+/- .0025
22	0.0299	+/- .003	0.0299	+/- .003	0.0336	+/- .004	0.0312	+/- .002	0.0253	+/- .002
23	0.0269	+/- .003	0.0269	+/- .003	0.0306	+/- .004	0.0281	+/- .002	0.0226	+/- .002
24	0.0239	+/- .003	0.0239	+/- .003	0.0276	+/- .004	0.025	+/- .0015	0.0201	+/- .002
25	0.0209	+/- .003	0.0209	+/- .003	0.0247	+/- .004	0.0219	+/- .0015	0.0179	+/- .002
26	0.0179	+/- .002	0.0179	+/- .002	0.0217	+/- .003	0.0187	+/- .0015	0.0159	+/- .0015
27	0.0164	+/- .002	0.0164	+/- .002	0.0202	+/- .003	0.0172	+/- .0015	0.0142	+/- .0015
28	0.0149	+/- .002	0.0149	+/- .002	0.0187	+/- .003	0.0156	+/- .0015	0.0126	+/- .0015
29	0.0135	+/- .002	0.0135		0.0172	+/- .003	0.0141		0.0113	+/- .0015
30	0.012	+/- .002	0.012		0.0157	+/- .003	0.0125		0.01	+/- .0015
31	0.0105		0.0105		0.0142		0.0109		0.0089	+/- .0015
32	0.0097		0.0097		0.0134		0.0102		0.008	+/- .0015
33	0.009		0.009				0.0094		0.0071	+/- .0015
34	0.0082		0.0082				0.0086		0.0063	+/- .0015
35	0.0075		0.0075				0.0078		0.0056	+/- .0015
36	0.0067		0.0067				0.007			—

Acier laminé à chaud (ALS), Acier laminé à froid (ALF),
Acier galvanisé (AG), Acier inoxydable (INOX), Aluminum (Alum)

TRIPARINC.COM